

THIRTEENTH ANNUAL CONFERENCE

YUCOMAT 2011

Hunguest Hotel Sun Resort Herceg Novi, Montenegro,
September 5-9, 2011
<http://www.mrs-serbia.org.rs>

Programme and The Book of Abstracts

Organised by:
Materials Research Society of Serbia

under the auspices of
Federation of European Material Societies
and
Materials Research Society

Title: THE THIRTEENTH ANNUAL CONFERENCE
YUCOMAT 2011
Programme and The Book of Abstracts

Publisher: Materials Research Society of Serbia
Knez Mihailova 35/IV, 11000 Belgrade, Serbia
Phone: +381 11 2185-437; Fax: + 381 11 2185-263
<http://www.mrs-serbia.org.rs>

Editor: Prof. Dr. Dragan P. Uskoković

Technical editor: Aleksandra Stojičić

Cover page: Aleksandra Stojičić and Milica Ševkušić

Copyright © 2011 Materials Research Society of Serbia

Acknowledgment:



Printed in: Biro Konto
Sutorina bb, Igalo – Herceg Novi, Montenegro
Phones: +382-31-670123, 670025, E-mail: bkonto@t-com.me
Circulation: 250 copies. The end of printing: August 2011

P.S.B.43.

**COROSION STUDIES OF NiMnGa SHAPE MEMORY ALLOYS
IN VARIOUS COROSIVE ENVIRONMENTS**

E. Szmidt¹, M. Grobelny¹, K. Sielicki², R. Wroblewski², M. Leonowicz²
¹*ITS, Warszawa, Polska,* ²*Faculty of Materials Science and Engineering,
Warsaw University of Technology, Warsaw, Poland*

Corrosion processes in metals substantially deteriorate their physico-chemical properties. The corrosive behaviour was studied in magnetic shape memory NiMnGa alloys. The process was investigated using voltamperometric method. Pure nickel was used as reference material. The measurements of open circuit potential (OCP) were applied for recording the dependence of current density I (A/cm^2) on the potential E (V), in the range of applied potential -150 mV to 1500 mV, at the potential velocity change of 1 mV/s. The measurements were carried out at room temperature, using solutions of NaCl, NaOH and H₂SO₄, respectively. It was found that the corrosion behaviour of NiMnGa alloys depends on the pH of the solution applied. The NiMnGa are more susceptible for corrosion than the pure nickel.

P.S.B.44.

MECHANOCHEMICAL SYNTHESIS OF Ba_{0.8}Sr_{0.2}TiO₃

D. Kosanović¹, S. Filipović¹, N. Obradović¹, M. Mitrić²,
S. Marković¹, A. Maričić³, V. Pavlović¹, M. M. Ristić⁴
¹*Institute of Technical Sciences of SASA, Belgrade, Serbia,* ²*The Vinča Institute, Condensed
Matter Physics Laboratory, Belgrade, Serbia,* ³*Technical Faculty Čačak, Čačak, Serbia,*
⁴*Serbian Academy of Sciences and Arts, Belgrade, Serbia*

Ba_{0.8}Sr_{0.2}TiO₃ was prepared from the starting materials BaCO₃, SrCO₃ and TiO₂ through solid state reaction. Mixtures of these oxides were mechanically activated using a high-energy ball mill at different time intervals from 0 to 120 minutes. X-ray diffraction was employed in order to determine the crystal structure and gave information about composition of phase variation. It was observed that after 40 minutes early synthesis of Ba_{0.8}Sr_{0.2}TiO₃ phase occurred. Particle size distribution along with scanning electron microscopy gave very useful information about powder morphology.