

Programme & The Book of Abstracts

Seventeenth Annual Conference

YUCOMAT 2015

Herceg Novi, Montenegro, August 31 – September 4, 2015

organised by

MATERIALS RESEARCH SOCIETY OF SERBIA

endorsed by



20th Anniversary YUCOMAT Conference

SEVENTEENTH ANNUAL CONFERENCE

YUCOMAT 2015

Hunguest Hotel Sun Resort Herceg Novi, Montenegro,
August 31-September 4, 2015
<http://www.mrs-serbia.org.rs>

Programme and The Book of Abstracts

Organised by:
Materials Research Society of Serbia

Endorsed by:
**Materials Research Society,
European Materials Research Society
and
Federation of European Material Societies**

Title: THE SEVENTEENTH ANNUAL CONFERENCE
YUCOMAT 2015
Programme and The Book of Abstracts

Publisher: Materials Research Society of Serbia
Knez Mihailova 35/IV, P.O.Box 433, 11000 Belgrade, Serbia
Phone: +381 11 2185-437; Fax: + 381 11 2185-263
<http://www.mrs-serbia.org.rs>


Editors: Prof. Dr. Dragan P. Uskoković and Prof. Dr. Velimir Radmilović

Technical editor: Aleksandra Stojičić

Cover page: Aleksandra Stojičić and Milica Ševkušić
Front cover: modified photo by BélaBéla; Wikimedia
(http://commons.wikimedia.org/wiki/File:Herceg_Novi.JPG); CC-BY-SA 3.0 Unported
Back cover: modified photo *Belgrade bridges* by mcveja; Flickr
(<https://www.flickr.com/photos/mcveja/2428406067/>); CC-BY 2.0 Generic

Copyright © 2015 Materials Research Society of Serbia

Acknowledgments: This conference is 20th Anniversary of the First YUCOMAT Conference.



Printed in: Biro Konto
Sutorina bb, Igalo – Herceg Novi, Montenegro
Phones: +382-31-670123, 670025, E-mail: bkonto@t-com.me
Circulation: 220 copies. The end of printing: August 2015

Influence of Sintering Atmosphere on the Crystal Structure, Microstructure, Dielectric and Optical Properties of $\text{BaTi}_{1-x}\text{Sn}_x\text{O}_3$ ($x = 0, 0.05$ and 0.1) Ceramics

Smilja Marković¹, Ljiljana Veselinović¹, Andrej Garaj²,
Nikola Cvjetičanin², Srečo D. Škapin³, Dragan Uskoković¹

¹*Institute of Technical Sciences of SASA, Belgrade, Serbia,* ²*Faculty of Physical Chemistry, University of Belgrade, Belgrade, Serbia,* ³*Jožef Stefan Institute, Ljubljana, Slovenia*

Due to specific dielectric and ferroelectric properties, functional ceramics based on barium titanate (BaTiO_3) have found application in semiconductor industries. Appropriate electrical properties of barium titanate-based materials, such as magnitude of relative dielectric permittivity and the Curie temperature, can be achieved by varying sintering conditions (which influenced ceramics' microstructure) and/or by doping with various cations.

In this study, we investigated the influence of sintering atmosphere (air and argon) on the crystal structure, microstructure, dielectric and optical properties of barium titanate-stannate (BTS; $\text{BaTi}_{1-x}\text{Sn}_x\text{O}_3$) ceramics. The BTS powders (with $x = 0, 0.05$ and 0.1 ; denoted BT, BTS5 and BTS 10, respectively) were synthesized by the solid-state reaction technique. The powders were subsequently uniaxially pressed ($P = 240$ MPa) into cylindrical compacts ($\varnothing 6$ mm and $h \approx 2$ mm) and sintered in SETSYS TMA (Setaram Instrumentation, Caluire, France). Sintering experiments were performed at a heating rate of 10 °/min up 1420 °C and with a dwell time of 2 hours; to determine the influence of sintering atmosphere, two sets of experiments were performed: (1) in air, and (2) in Ar. During sintering, the shrinkage was recorded in the axial (h) direction. The crystal structure of the BTS ceramics was studied at room temperature by X-ray diffractometry and Raman spectroscopy. The microstructure and chemical (Ti/Sn) composition were examined by SEM-EDS methods. The electrical measurements were made in air, at 1 kHz using a Wayne Kerr Universal Bridge B224; the measurements were done in cooling, from 160 to 20 °C. For optical characterization UV-Vis diffusive reflectance and photoluminescence spectroscopy were employed. A profound effect of an argon atmosphere on the examined properties of the sintered BTS ceramics has been found; the mostly important is an increase of the magnitude of relative dielectric permittivity.